


K04-P



Ordering dimensions in **blue**

Surface roughness	R_{tmax}	R_a
Sliding surface	$\leq 2,5 \mu m$	$0,05-0,2 \mu m$
Bottom of groove	$\leq 6,3 \mu m$	$\leq 1,6 \mu m$
Groove face	$\leq 15 \mu m$	$\leq 3 \mu m$

Bearing area: 50–95% and a cutting depth of $0,5 R_z$, based on $C_{ref} = 0\%$

Standard dimensions						Maximal radial extrusion gap			
D	H9	d	L	R_{max}	c	s^*			
over	incl.	h10	+ 0,2			20 bar	100 bar	400 bar	700 bar
mm						mm			
13	25	D - 8	6,0	0,4	3,5	0,80	0,80	0,30	0,04
25	50	D - 10	7,0	0,4	4,0	1,00	1,00	0,37	0,04
50	75	D - 12	8,0	0,4	4,5	1,25	1,24	0,42	0,05
75	150	D - 15	10,0	0,4	5,0	1,50	1,47	0,46	0,05
150	300	D - 20	12,0	0,4	6,0	2,00	1,77	0,54	0,06
300	500	D - 25	18,0	0,4	8,5	2,50	2,06	0,62	0,06
500	600	D - 30	20,0	0,4	10,0	3,00	2,43	0,76	0,06
600	1000	D - 40	26,0	0,4	13,0	3,00	2,43	0,76	²⁾
1000	1600	D - 50	32,0	0,4	15,0	3,00	2,43	0,76	²⁾

¹⁾ Extrusion gap values shown above are valid for a temperature of 70 °C, higher temperatures require lower values.

²⁾ Please contact SKF.

Ordering example

Profile
D x d x L [mm]
Sealing material / Energizer / Backup ring

Piston seal K04-P
100 x 85 x 10
ECOPUR / NBR70 / SKF Ecotal

Operating parameters

Material Seal	Energizer	Back-up ring	Temperature		Speed ¹⁾	Pressure ²⁾
			from	to	max	max
–			°C		m/s	bar (MPa)
■ ECOPUR	NBR70	■ SKF Ecotal ³⁾ ■ SKF Ecomid ³⁾	–30	+100	0,5	700 (70)
■ ECOPUR LD		■ SKF Ecomid				
■ G-ECOPUR						
■ H-ECOPUR	MVQ70	■ SKF Ecotal ³⁾ ■ SKF Ecomid ³⁾	–20		0,7	
■ S-ECOPUR						
■ T-ECOPUR				–40		0,5

IMPORTANT NOTE: The stated operating conditions represent general indications. It is recommended not to use all maximum values simultaneously.

¹⁾ Surface speed limit values are valid only in the presence of a lubrication film.

²⁾ Pressure ratings depend on the size of the extrusion gap.

³⁾ D ≤ 260 mm → SKF Ecotal, D > 260 mm → SKF Ecomid.