


# SKF Ecomid

## Cast polyamide 6 (PA6)

Property	Unit	Value	Standard
Standard color	–	Black/natural 	
Durometer hardness	Shore D	77	ISO 868
Density	g/cm <sup>3</sup>	1,15	DIN EN ISO 1183-1
Yield stress, saturated	MPa	55	ISO 527-1/2
Elongation at break, saturated	%	100	ISO 527-1/2
Tensile modulus, saturated	MPa	1 800	ISO 527-1/2
Impact resistance, charpy, 23 °C, saturated	kJ/m <sup>2</sup>	no break	ISO 179-1
Water absorption, 23 °C, saturation	%	8,5	ISO 62
Moisture absorption, 23 °C, saturation	%	2,2	–
Coefficient of sliding	–	0,35–0,42	–
Minimum service temperature	°C	–40	–
Maximum service temperature	°C	+110	–

IMPORTANT NOTE: The values shown above are only valid for material samples prepared for test purposes according to the stated standards.

© SKF is a registered trademark of the SKF Group.

© SKF Group 2014

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless prior written permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of the use of the information contained herein.

PUB SE/P8 12477/1 EN · October 2014

